

**ZACK PLAS**

PIPE EXTRUSION & INJECTION MOULDING

PRODUCT TECHNICAL DATA

Product: 8/5mm	Bundle: 1 way	Micro Duct – Direct burial
Product supply: 2000m	Type: reel / drum	Wall thickness: 1.5mm
Inner diameter: 5mm	Outer diameter: 8mm	

Characteristics	
Construction	Outer layer: HDPE Inner layer: Silicone
Material	HDPE (Polyethylene)

Properties	
Ovality	<5%
Pressure Rating	12 bar for 5 minutes
Coefficient of Friction	(Less than one)
Ball Testing	80% of inside diameter, ball passes freely
Chemical Resistance	Petrol, Diesel, Acetone, Ingepol
Colour	RAL Codes
Kink Test	Passes
Bending Radii	20 x outside diameter

Handling & Storage	
Storage Temperature	-20 °C to +60 °C
Installation Temperature	+15 °C to +40 °C
UV Resistance Period	1-year outdoor storage
Installation	As per SABS 1200LB

Material Properties	Values	Test Method
Melt Index (190°C/2.16kg)	0.40g/10 minutes	ASTM D1238
Density	0.941 – 0.957g/cm ³	ASTM D1505
Vicat Softening Point @ 10 N, 50°C/hr	125 °C	ASTM D1525
Melting Point	133 °C	ASTM D2117
Tensile Strength at Yield Point	320kg/ m ³	ASTM D638
Tensile Strength at Break Point	400kg/ m ³	ASTM D638
Elongation at Break	1000%	ASTM D638
Stiffness	10,000kg/ m ²	ASTM D747
Flexural Modulus	14,000kg/ m ²	ASTM D790
Notched Izod Impact Strength	15kg.cm/cm – Partial Break	ASTM D256
Durometer Hardness	65 Shore D	ASTM D2240
ESCR (Condition B, 25% Ingepol)	400hrs, F50	ASTM D1693



One-way
(Profile System)

ZACK PLAS - Pipe extrusion & injection mouldingHead Office: 5 Marconi Crescent, Montague Gardens, 7441, Cape Town | Tel: +27(0) 82 450 0997 (Joop Robbertse) | E-mail: info@zackplas.co.za