



PRODUCT TECHNICAL DATA

| Product: 8/5mm | Bundle: 2 way | Bundled Duct - Direct burial |
|-----------------------|---------------------|------------------------------|
| Product supply: 2000m | Type: reel / drum | Wall thickness: 1mm |
| Inner diameter: 5mm | Outer diameter: 8mm | |

| Characteristics | | |
|-----------------|---|--|
| Construction | Outer layer: HDPE Inner layer: Silicone | |
| Material | HDPE (Polyethylene) | |

| 1 2 | 1 | 2 |
|-----|---|---|
|-----|---|---|

| Properties | |
|-------------------------|--|
| Ovality | <5% |
| Pressure Rating | 12 bar for 5 minutes - Inner ducts |
| Coefficient of Friction | (Less than one) |
| Ball Testing | 80% of inside diameter, ball passes freely |
| Chemical Resistance | Petrol, Diesel, Acetone, Ingepol |
| Colour | RAL Codes |
| Kink Test | Passes |
| Bending Radii | 20 x outside diameter |

Two-way (Profile system with protective sheath)

| Handling & Storage | |
|--------------------------|------------------------|
| Storage Temperature | -20 °C to +60 °C |
| Installation Temperature | +15 °C to +40 °C |
| UV Resistance Period | 1-year outdoor storage |
| Installation | As per SABS 1200LB |

| Material Properties | Values | Test Method |
|---------------------------------------|----------------------------|-------------|
| Melt Index (190°C/2.16kg) | 0.40g/10 minutes | ASTM D1238 |
| Density | 0.941 - 0.957g/cm³ | ASTM D1505 |
| Vicat Softening Point @ 10 N, 50°C/hr | 125 °C | ASTM D1525 |
| Melting Point | 133 °C | ASTM D2117 |
| Tensile Strength at Yield Point | 320kg/ m ³ | ASTM D638 |
| Tensile Strength at Break Point | 400kg/ m ³ | ASTM D638 |
| Elongation at Break | 1000% | ASTM D638 |
| Stiffness | 10,000kg/ m ² | ASTM D747 |
| Flexural Modulus | 14,000kg/ m ² | ASTM D790 |
| Notched Izod Impact Strength | 15kg.cm/cm – Partial Break | ASTM D256 |
| Durometer Hardness | 65 Shore D | ASTM D2240 |
| ESCR (Condition B, 25% Ingepol) | 400hrs, F50 | ASTM D1693 |

ZACK PLAS - Pipe extrusion & injection moulding